

### Pearlescent paint with old metal surface effect

*Water dispersion interior paint*

#### INTENDED USE

**BALITURA OXY METALLO** is an interior water dispersion paint with monochrome pearl microparticles embedded in it. It is available in 4 colours /combined in a 2x2 box/, factory prepared and tinted to guarantee consistency of quality and colour. The extremely beautiful and elegant look, reminiscent of old patinated surfaces and the rich colour possibilities from the iridescence of multicoloured "rusts", give a huge variety of design solutions and make **BALITURA OXY METALLO** the perfect touch for any modern home.

The purpose of the paint is to make a fine decorative coating on walls and ceilings of interior rooms. It has short drying times and excellent coverage. One litre of paint is sufficient for up to 4 m<sup>2</sup>.

**BALITURA OXY METALLO** is water soluble, harmless and does not contain solvents, volatile organic compounds and chemical ingredients hazardous to health and the environment.

#### PROPERTIES

- ❖ ready to use
- ❖ excellent coverage
- ❖ easy to apply
- ❖ short drying time
- ❖ non-toxic

#### SURFACE PREPARATION

**BALITURA OXY METALLO** is suitable for work on gypsum plaster and gypsum plasterboard substrates, after mandatory priming. The substrate must be smooth, dry and well cleaned. The joints in plasterboard must be filled and the boards plastered. Old paint or other non-load bearing coatings must be washed or mechanically removed.

To equalize the absorption capacity, improve adhesion, dedusting, and unify the color with that of the paint, the substrate should be primed with the included specially developed primer **BALITURA FONDO**, tinted in dark gray color.



#### LAYING AND PROCESSING

**BALITURA OXY METALLO** is ready for use once it has been stirred to achieve a homogeneous colour. The use of paper tape is recommended to protect adjacent walls or existing flooring.

**BALITURA OXY METALLO** is applied with the two colours alternately by overlapping and layering (wet-in-wet) using a porous sponge. Work continuously, edge to edge, with short "tapping" movements. The product is ready for use without dilution.

The drying time of the applied layer is about 6 hours.

#### CONSUMPTION

- approx. 0,220 – 0,330 l/m<sup>2</sup>

#### WORKING TOOLS

- paper tape
- porous sponge

#### ATMOSPHERIC WORKING CONDITIONS

The product is intended for interior use. The minimum daytime air and substrate temperature should not be lower than +5°C and the maximum temperature should not be higher than +30°C.

#### DELIVERY PACKAGING

Three plastic packs per carton. Set includes 2 pieces of paint and 1 piece of primer.

# TECHNICAL DATA SHEET

## BALITURA OXY METALLO

### NOTES

The product characteristics and technical data specified in this process card are determined at standard temperature (20°C) and relative humidity (50%). Under other climatic conditions, the process times for some of the above processes may be shortened or extended.

The product information is based on the manufacturer's practical experience and technical tests in specialized laboratories.

decorative paint®  
**Balitura**

Do not mix with other construction materials.

All warnings and safety recommendations regarding **BALITURA OXY METALLO** can be checked in the Product Safety Data Sheet.

### STORAGE

24 months in original sealed packaging at temperatures from +5°C to +30°C. Keep away from frost and direct sunlight.

### CHARACTERISTICS AND TECHNICAL DATA

|                                    |                                                                  |
|------------------------------------|------------------------------------------------------------------|
| Color                              | By catalogue                                                     |
| Form (aggregate state)             | liquid                                                           |
| Drying time                        | 6 hours                                                          |
| Density                            | 1,44 g/cm <sup>3</sup>                                           |
| Adhesion to substrate              | 3,19 N/mm <sup>2</sup>                                           |
| pH - value                         | 7,8                                                              |
| Content of non-volatile substances | 62,62 %                                                          |
| Water permeability coefficient – w | 0,23 kg/m <sup>2</sup> .h <sup>0,5</sup> (class W <sub>2</sub> ) |

The manufacturer is responsible for the quality of the product, but not for the manner and conditions of its application. The information in this technical data sheet is reliable provided that the product is used under the specified conditions. Any other use of the product, including use in combination with another product or process, is the sole responsibility of the user.